

DOCTORAL THESIS

Au/CeO₂ based catalysts for catalytic oxidation of volatile organic compounds and carbon monoxide

Ying, Fang

Date of Award:
2010

[Link to publication](#)

General rights

Copyright and intellectual property rights for the publications made accessible in HKBU Scholars are retained by the authors and/or other copyright owners. In addition to the restrictions prescribed by the Copyright Ordinance of Hong Kong, all users and readers must also observe the following terms of use:

- Users may download and print one copy of any publication from HKBU Scholars for the purpose of private study or research
- Users cannot further distribute the material or use it for any profit-making activity or commercial gain
- To share publications in HKBU Scholars with others, users are welcome to freely distribute the permanent URL assigned to the publication

**Au/CeO₂ Based Catalysts for Catalytic Oxidation of Volatile
Organic Compounds and Carbon Monoxide**

YING Fang

**A thesis submitted in partial fulfillment of the requirements
for the degree of
Doctor of Philosophy**

Principal Supervisor: Dr. Lai Suk Yin

Hong Kong Baptist University

May 2010

ABSTRACT

Catalytic complete oxidation of CO and VOCs is one of the most efficient ways for the abatement of air pollution. It is crucial to prepare catalysts with high activity and long-term stability for practical use. In this work, gold supported on 3-D mesoporous CeO₂, 3-D mesoporous CeO₂-Fe₂O₃, 1-D mesoporous ceria, ceria nanopolyhedra, nanorods and nanocubes as catalysts for CO, butane and benzene complete oxidation have been investigated. The catalysts were characterized in details by various techniques, including ICP-AES, N₂ adsorption-desorption, XRD, XPS, DR UV-Vis, SEM, TEM, EDS, TOF-SIMS, EPR, TPR and TPD, to elucidate the structure-activity relationship.

It was found that the ceria morphology has a profound effect on CO and isobutane oxidation reactions. Ceria nanorods (11.1 nm in diameter) enclosed by (110) and (100) planes showed higher activity than nanocubes (27.5 nm in diameter) bounded by (100) planes, while nanopolyhedra (6.1 nm in diameter) with exposure of (111) planes exhibited the lowest specific reaction rate. The lower activity of nanopolyhedra was ascribed to the fewer number of active surface oxygen species that can be provided on (111) planes. On the contrary, benzene oxidation activity increased with the decrease in ceria particle size and nanopolyhedra showed the highest activity due to its smaller particle size. The deposition of gold significantly enhanced the activity of the surface oxygen and the oxidation activity of ceria. Furthermore, gold dispersion was found to increase with the decrease in ceria particle size. Au/CeO₂-rod exhibited the highest CO oxidation activity due to the synergetic effects arising from the nanosized gold and the well-defined surface of nanorods. Au/CeO₂-polyhedron showed the highest activity in isobutane and benzene oxidation reactions due to its

relatively small ceria particle size and high gold dispersion.

The role of cationic gold in CO and butane oxidation reactions was also investigated. Au/CeO₂ catalysts with different fraction of cationic gold and similar ceria support were prepared. The results suggested that the reducibility of the surface oxygen on ceria can be enhanced by cationic gold species more efficiently than metallic gold and the CO oxidation activity increased with the increasing fraction of cationic gold species. In butane oxidation, the Au⁺ species formed under reaction conditions as surface gold oxide was responsible for the low temperature activity over Au/ceria, while the high temperature activity was enhanced by substitutional Au³⁺ ions.

Since nanosized ceria facilitates the dispersion of gold and the ceria size effect was more profound than morphology effect in benzene oxidation, it is desirable to prepared nano-size ceria supported gold catalysts for VOCs oxidation. In this work, 3-D (CeO₂-48) and 1-D (CeO₂-41) ordered mesoporous ceria materials supported gold catalysts were prepared. CeO₂-48 (3 nm in diameter) and CeO₂-41 (4 nm in diameter) exhibited smaller particle size, larger specific surface area and higher concentration of surface oxygen vacancies than that of alkaline precipitated ceria sample CeO₂-P (7-14 nm in diameter). Superoxide on ceria was found to be the active species for low temperature benzene oxidation. CeO₂-48 with higher Ce³⁺ and oxygen vacancy concentration can stabilize superoxide species at higher temperature than CeO₂-P, thereby achieving higher benzene oxidation activity. Au/CeO₂-48 exhibited excellent benzene oxidation activity with T₅₀ achieved at 151 °C. More importantly, CeO₂-48 with higher amount of structural defects generated after the removal of silica can stabilize gold species better than Au/CeO₂-P. Hence Au/CeO₂-48 showed much higher long-term stability than Au/CeO₂-P.

The physicochemical properties of CeO₂-48 were modified by iron. 3-D mesoporous Fe₂O₃ and Ce-Fe mixed oxide with high surface area (higher than 100 m²g⁻¹) and very small particle size were synthesized through a hard template method. XRD data confirmed the formation of cubic Ce_xFe_{1-x}O₂ and hematite-like solid solution in Ce-Fe mixed oxide. It was found that higher surface oxygen reducibility and higher oxygen mobility were achieved in Ce-Fe mixed oxide than in single CeO₂ or Fe₂O₃, leading to higher CO and isobutane oxidation activity on Ce-Fe mixed oxide. This was due to the weakening of metal-oxygen bonds in the solid solution and the generation of bulk oxygen vacancies by the substitution of Ce⁴⁺ by Fe³⁺. However, the addition of Fe enhanced the evolution from superoxide to other adsorbed oxygen species. Therefore, Ce-Fe mixed oxides showed lower activity than CeO₂-48 in benzene oxidation. For supported gold catalysts, CO and benzene oxidation activity decreased with the increase of Fe content in the support of Au/Ce-Fe, indicating that the interaction between Au-Ce was stronger than that between Au-Fe. On the other hand, Au/CeFe(2:1) achieved 100% isobutane conversion at temperature below 300 °C, while complete oxidation of isobutane was not reached at 500 °C over Au/CeO₂-48. TPR results indicated that the deposition of gold on ceria mainly increased the activity of surface oxygen, while both surface oxygen activity and lattice oxygen mobility was enhanced on Ce-Fe mixed oxides. This suggested that CO and benzene can be oxidized by active surface oxygen species, while both adsorbed oxygen species and lattice oxygen were important for isobutane oxidation.

Key word: CO oxidation, VOCs oxidation, gold, CeO₂, nanopolyhedron, nanorod, nanocube, Ce-Fe mixed oxide

TABLE OF CONTENTS

DECLARATION	i
ABSTRACT	ii
ACKNOWLEDGEMENT	v
TABLE OF CONTENTS	vi
LIST OF TABLES	xi
LIST OF FIGURES	xiii
CHAPTER I Introduction	1
1.1 Background	1
1.2 Catalytic Oxidation of VOCs	3
1.2.1 Catalysts Systems	3
1.2.1.1 Supported Noble Metals	4
1.2.1.2 Transition Metal Oxides.....	5
1.2.1.3 Perovskites	7
1.2.2 Mechanisms	11
1.3 CO Oxidation	12
1.3.1 Catalysts	13
1.3.2 Mechanisms	13
1.4 Ceria-based Catalyst Systems	16
1.4.1 Particle Size Effect	17
1.4.2 Morphology Effect	18
1.4.3 Effects of Additives	18

1.4.4 Preparation Methods for Nanocrystalline Ceria	19
1.4.4.1 Mesoporous Ceria	20
1.4.4.2 Morphology Controlled Synthesis of Ceria	22
1.4.4.3 Ce-Siliceous Mesoporous Materials	24
1.5 Au/Ceria Systems	25
1.5.1 Effect of Gold Particle Size	27
1.5.2 Effect of Gold Oxidation State	28
1.5.3 Effect of Gold-Support Interaction	30
1.6 Au/iron Oxide	31
1.7 Scope of Study	32
Reference	34
CHAPTER II Experimetal	51
2.1 Catalysts Preparation	51
2.2 Catalysts Evaluation	52
2.3 Characterization	53
2.3.1 Scannis Electyron Microscopy	54
2.3.2 Transmission Electron Microscopy	54
2.3.3 N₂ Adsorption-desorption	55
2.3.4 X-ray Diffreaction Analysis	56
2.3.5 X-ray Photoelectron Spectroscopy	58
2.3.6 Electron Paramagnetic Resonance	59
2.3.7 Inductively Coupled Plasma-Optical Emission Spectrometer 60	
2.3.8 H₂ Temperature-programmed Reduction	60
2.3.9 Benzene Temperature-programmed Desorption	61
2.3.10 Time-of-Flight Secondary Ion Mass Spectroscopy	62

2.3.11 Ultraviolet-visible Diffuse Reflectance Spectroscopy	63
Reference	64
CHAPTER III Effect of CeO₂ Morphology on CO and VOCs Complete Oxidation on Au/CeO₂ System.....	66
3.1 Introduction.....	66
3.2 Catalysts Preparation.....	69
3.3 Results and Discussion.....	71
3.3.1 Morphology Characterization	71
3.3.2 XPS.....	77
3.3.3 DR VU-Vis	84
3.3.4 H ₂ -TPR.....	85
3.3.5 Catalytic Test.....	89
3.4 Conclusion	97
Reference	98
CHAPTER IV Effect of Oxidation State of Gold on the Complete Oxidation of COand VOCs on Au/CeO₂ Catalysts.....	103
4.1 Introduction.....	103
4.2 Catalysts Preparation.....	105
4.3 Results and Discussion.....	106
4.3.1 Morphological and Structural Characterization	106
4.3.2 Surface Chemical State.....	110
4.3.3 H ₂ -TPR.....	115
4.3.4 Catalytic Activity.....	118
4.3.5 The Importance of Cationic Gold in Isobutane Oxidation Reaction	

.....	125
4.3.6 Origin of the Cationic Gold Species	129
4.3.7 Nature of the Active Sites for Isobutane Oxidation	130
4.4 Conclusion	131
Reference	133
 CHAPTER V Mesoporous CeO₂ Supported Au Catalysts on CO and VOCs	
Complete Oxidation.....	137
5.1 Introduction.....	137
5.2 Catalysts Preparation.....	140
5.3 Results and Discussion.....	143
5.3.1 TEM	143
5.3.2 XRD.....	148
5.3.3 Textural Properties.....	152
5.3.4 XPS.....	156
5.3.5 TOF-SSIMS	161
5.3.6 H ₂ -TPR.....	162
5.3.7 EPR	166
5.3.8 Catalytic Activity.....	169
5.3.9 Effect of Mesoporous Structure of Ceria on the Benzene Oxidation	174
5.3.10 Catalytic Stability Test.....	176
5.4 Conclusion	178
Reference	180
 CHAPTER VI Au Supported on Three-dimensional Mesoporous Ce-Fe Oxide for CO and VOCs Complete Oxidation	
	184

6.1 Introduction	184
6.2 Catalysts Preparation	186
6.3 Results and Discussion	187
6.3.1 XRD	187
6.3.2 N₂ Adsorption-desorption	190
6.3.3 HRTEM	193
6.3.4 Surface Composition	195
6.3.5 TOF-SSIMS	203
6.3.6 H₂-TPR	206
6.3.7 Catalytic Activity	210
6.3.8 Nature of the Active Sites for the Different Reaction	214
6.3.8.1 CO Oxidation.....	214
6.3.8.2 Benzene Oxidation.....	215
6.3.8.3 Isobutane Oxidation.....	216
6.4 Conclusion	218
Reference	219
CHAPTER VII Conclusion and Future Work	222
7.1 Conclusion	222
7.1.1 Investigation on Ceria Morphology Effect	222
7.1.2 Investigation on the Effect of Oxidation State of Gold	223
7.1.3 Preparation of Highly Active and Long-term Stable Catalysts	224
7.2 Future Work	226
Reference	228
CURRICULUM VITAE	229