

DOCTORAL THESIS

Synthesis, characterization and optoelectronic applications of new conjugated organic and organometallic polymers

Zhan, Hongmei

Date of Award:
2011

[Link to publication](#)

General rights

Copyright and intellectual property rights for the publications made accessible in HKBU Scholars are retained by the authors and/or other copyright owners. In addition to the restrictions prescribed by the Copyright Ordinance of Hong Kong, all users and readers must also observe the following terms of use:

- Users may download and print one copy of any publication from HKBU Scholars for the purpose of private study or research
- Users cannot further distribute the material or use it for any profit-making activity or commercial gain
- To share publications in HKBU Scholars with others, users are welcome to freely distribute the permanent URL assigned to the publication

Synthesis, Characterization and Optoelectronic Applications of New Conjugated Organic and Organometallic Polymers

ZHAN Hongmei

**A thesis submitted in partial fulfillment of the requirements
for the degree of
Doctor of Philosophy**

Principal Supervisor: Professor WONG Wai Yeung, Raymond

Hong Kong Baptist University

May 2011

Abstract

Polymer solar cells have attracted considerable attention for the potential application as renewable energy sources due to their unique advantages of the ease of solution-processing, low cost, light weight and flexible large-area devices, and encouraging progress has been made in the past decade. Metal-containing conjugated polymers represent an intriguing and promising class of materials, and platinum polyynes have been shown to be good candidates for organic solar cells. Organic conjugated polymers as the other important type of materials have also been extensively studied in the field of solar cells, and show outstanding performance.

New series of metal-containing polymers based on different π -conjugated chromophores and a new type of organic conjugated polymers with lower band gaps were synthesized and fully characterized. The applications of some of these polymers in solar cells or field-effect transistors are also outlined.

Chapter 1 contains a brief overview on the background, basic theory and development of bulk-heterojunction (BHJ) solar cells.

Chapter 2 presents the synthesis and characterization of a new series of platinum(II)-containing conjugated polymers based on pyran, diketopyrrolopyrrole, benzothiadiazole or thiadiazolo[3,4-*c*]pyridine, fluorene and phenanthrenyl-imidazole chromophores, typically designed via a donor-acceptor (D-A) approach. These polymers were synthesized by Sonogashira-type dehydrochloride reaction between the diethynyl ligands and *trans*-Pt(PBu₃)₂Cl₂. Their photophysical properties were

fully investigated by the UV-vis and PL spectroscopies. In addition, the HOMO and LUMO energy levels of all the polymers were tested by cyclic voltammetry. The band gap of polymers can be tuned by changing the electron-donating ability of donor unit or the electron-withdrawing ability of acceptor unit in a D-A system. Some of the platinum polyynes have been fabricated into photovoltaic devices and showed the power conversion efficiency (PCE) up to 1.4%.

A full account of the preparation, characterization, photophysical and thermal properties of a new series of organometallic polymers based on zinc(II)-porphyrin and platinum(II) alkynyls are presented in Chapter 3. These polymers exhibit a strong Soret band at ca. 430 nm and two weak Q-bands between 540 nm and 635 nm, which is a typical absorption profile for porphyrin compounds. The frontier molecular orbitals for their corresponding oligomeric model compounds were fully investigated by DFT and TDDFT. Photovoltaic devices based on these polymers were fabricated and showed good photovoltaic performance.

In Chapter 4, a new series of organic conjugated polymers based on cyclopentadithiophene and thiadiazolo-[3,4-*c*]pyridine or pyridine were designed and synthesized by the novel microwave-assisted Stille-coupling reaction. Most of these polymers show better absorption properties in the visible and near-infrared region. The charge carrier mobilities of some of them were investigated by organic field-effect transistors. This series of polymers showed higher charge carrier mobilities, the highest value reaching up to $0.022 \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$ for hole mobility and $0.12 \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$ for electron mobility, presented by the regioregular polymer **P21**.

Chapters 5 and 6 present the concluding remarks and the experimental details of the work described in Chapters 2–4.

Table of Contents

Declaration		i
Abstract		ii
Acknowledgements		v
Table of Contents		vii
List of Tables		xii
List of Figures		xiv
List of Schemes		xx
List of Abbreviations and Symbols		xxii
Formula Index		xxvii
Chapter 1	Introduction	1
1.1	Background	1
1.2	Basic Working Principles of Organic Solar Cells	4
1.3	Organic Photovoltaic Device Architectures	9
1.4	Development of Organic Solar Cells	11
1.4.1	New Electron Donor Materials	14
1.4.2	New Electron Acceptor Materials	24
1.4.3	New Technologies Based on Solar Cell Architectural Designs	26
1.4.4	Optimization of the Morphology of the Active Layer	28
1.5	Summary and Future Perspectives	30

	References	33
Chapter 2	Synthesis, Characterization and Photovoltaic Properties of a New Series of Conjugated Platinum Polyynes for Use in Solar Cells	39
2.1	Introduction	39
2.2	Synthesis	44
2.2.1	Design and Synthesis of Pyran Based Platinum Polyynes	44
2.2.2	Design and Synthesis of Diketopyrrolopyrrole Based Platinum Polyynes	56
2.2.3	Design and Synthesis of Benzothiadiazole or Thiadiazolopyridine Based Platinum Polyynes	62
2.2.4	Design and Synthesis of Fluorene Based Platinum Polyynes	69
2.2.5	Design and Synthesis of Phenanthrenyl-Imidazole Based Platinum Polyynes	75
2.3	Spectroscopic Characterization	79
2.4	Optical Absorption and Photoluminescence Spectroscopies	93
2.5	Thermal Gravimetric Analysis and Molecular Weight Determination of Metallopolyyne Polymers	118
2.6	Redox Properties of Metallopolyyne Polymers	121
2.7	Photovoltaic Performance of Metallopolyyne Polymers	125
2.8	Conclusions	138

	References	141
Chapter 3	Synthesis, Characterization and Photovoltaic Properties of New Metalloporphyrin-Containing Polyplatinyne Polymers	150
3.1	Introduction	150
3.2	Synthesis	153
3.3	Spectroscopic Characterization	157
3.4	Optical Absorption and Photoluminescence Spectroscopies	163
3.5	Spectroscopic and Computational Details	169
3.6	Thermal Gravimetric Analysis and Molecular Weight Determination of Metallopolyyne Polymers	179
3.7	Redox Properties of Metallopolyyne Polymers	180
3.8	Photovoltaic Performance of Metallopolyyne Polymers	182
3.9	Concluding Remarks	186
	References	188
Chapter 4	Synthesis, Characterization and Charge Carrier Mobility Studies of Conjugated Organic Polymers Based on Cyclopentadithiophene and Pyridalthiadiazole or Pyridine Chromophores	193
4.1	Background	193
4.2	Synthesis	197
4.2.1	Synthesis of Regioregular Polymers P21 and P22	197

4.2.2	Synthesis of Organic Polymer P23	203
4.2.3	Synthesis of Organic Polymer P24	204
4.3	Spectroscopic Characterization	205
4.4	Optical Properties	211
4.5	Thermal Gravimetric Analysis and Molecular Weight Determination of Organic Polymers	217
4.6	Electrochemical Properties	218
4.7	Carrier Mobility Studies for OFET	220
4.8	Conclusions	224
	References	226
Chapter 5	Conclusions and Future Work	229
Chapter 6	Experimental Details	234
6.1	General	234
6.2	Materials	237
6.3	Experimental Details for Chapter 2	237
6.3.1	Experimental Details for Organometallic Polymers Based on Pyran Chromophore	237
6.3.2	Experimental Details for Organometallic Polymers Based on DPP Chromophore	257

6.3.4	Experimental Details for Organometallic Polymers Based on Fluorene Chromophore	283
6.3.5	Experimental Details for Organometallic Polymers Based on Phenanthrenyl-Imidazole Chromophore	295
6.4	Experimental Details for Chapter 3	308
6.5	Experimental Details for Chapter 4	320
	References	328
	Curriculum Vitae	330