

DOCTORAL THESIS

Synthesis and characterization of novel thienoacene-based semiconductors for transistors and dye-sensitized solar cell applications

Zhang, Kai

Date of Award:
2016

[Link to publication](#)

General rights

Copyright and intellectual property rights for the publications made accessible in HKBU Scholars are retained by the authors and/or other copyright owners. In addition to the restrictions prescribed by the Copyright Ordinance of Hong Kong, all users and readers must also observe the following terms of use:

- Users may download and print one copy of any publication from HKBU Scholars for the purpose of private study or research
- Users cannot further distribute the material or use it for any profit-making activity or commercial gain
- To share publications in HKBU Scholars with others, users are welcome to freely distribute the permanent URL assigned to the publication

Abstract

Organic field-effect transistors (OFET) have attracted considerable interests as a promising technology for the next-generation flexible electronics. Thioacenes have recently emerged as potential semiconducting materials for OFETs. On the other hand, Photovoltaic (PV) technology is regarded as a prospective alternative for green and renewable energy source. Recently, dye sensitized solar cells (DSSCs) have drawn intensive attention and showed great potential for practical application. Herein, the research in this thesis would include the synthesis and characterization of novel thioacene-based semiconductors for OFET and DSSC applications.

To begin with, a general review on the current status of organic semiconductors for OFET and DSSC applications was presented in Chapter 1.

In chapter 2, a series of novel benzodithieno[3,2-*b*]thiophene derivatives (**BDTT-n**) with different lateral alkyloxy groups were designed and synthesized. In addition, alkyloxy-substituted benzo[2,1-*b*:3,4-*b'*]bis-[1]benzothiophenes derivatives (**BBBT-n**) were also synthesized. The performances of OFETs based on **BDTT-n** and **BBBT-n** have been fully investigated. Among them, **BDTT-4** based OFET exhibited the highest hole mobility of $1.74 \text{ cm}^2/(\text{Vs})$ with a current on/off ratio above 10^7 without annealing.

In chapter 3, a novel series of naphthodithiophene-based oligomers with D-A-D-A-D structure motif were designed and synthesized. All these oligomers have been fully characterized by NMR and mass spectrometry. The hole mobility properties of these oligomers were determined in OFETs as fabricated by drop-coating technique. These oligomers exhibited typical p-type semiconducting behavior. A mobility of $1.6 \times 10^{-2} \text{ cm}^2/(\text{Vs})$ was demonstrated by **ENBT** based OFET with a current on/off ratio in the range of 10^{5-7} after annealing at 160 °C.

Besides, in chapter 4, a novel π -bridge, namely naphthodithienothiophene was developed and employed to explore photosensitizers for DSSC application. In this work, four novel photosensitizers with D-A- π -A or D- π -A structure motif were designed and synthesized in which the carbazole or triphenylamine derivative was used as a donating group and benzothiadiazole was applied as auxiliary accepting group. The performances of DSSCs based on these photosensitizers have been fully investigated. Among them, **CB-NDTT-CA** based device exhibited the highest power conversion efficiency (PCE) of 7.29%. Meanwhile, the interfacial properties of these photosensitizers anchored on TiO₂ have also been studied by *ab-initio* simulation and Gaussian calculations.

In chapter 5, another novel series of photosensitizers with benzodithienothiophene as the π -bridge would be presented, in which different donors, auxiliary acceptors, and structures were incorporated into the frameworks

of D- π -A motif to investigate the relationship between the structure and properties. The performances of DSSCs based on these photosensitizers have been fully investigated, and **BD-5** based device exhibited the best power conversion efficiency (PCE) of 4.66%. Furthermore, it was demonstrated that molecular engineering was an efficient way to modulate the performance of the DSSCs in which benzothiadiazole was used as an effective auxiliary accepting group in constructing photosensitizers with D-A- π -A structure motif. The di-anchoring approach was also found to be a promising method to design photosensitizers with improved performance.

Key words: organic semiconductors, organic field-effect transistor, photosensitizers, DSSCs, naphdithienothiophene, benzodithienothiophen, naphdithiophene.

Table of Contents

Declaration	i
Abstract.....	ii
Formula Index.....	v
Table of Contents.....	x
List of Figures.....	xvi
List of Tables	xxii
List of Schemes.....	xxiv
List of Abbreviation and Symbols.....	xxvi
Chapter 1 Introduction Organic Transistors and Dye Sensitized Solar Cells	
1	
1.1 Introduction.....	1
1.1.1 Introduction to organic semiconductors.....	2
1.1.1.1 Basic operation of organic field effect transistors	3
1.1.1.2 Electrical characterization of OFTTs	5
1.1.1.3 Energy level of organic semiconductors.....	6
1.1.1.4 Packing-state of organic semiconductors.....	9

1.1.1.5	Fabrication of organic transistors.....	10
1.1.1.6	Organic semiconductors for OFETs.....	12
1.1.2	Introduction to DSSCs	24
1.1.2.1	Operation principle	26
1.1.2.2	Characteristics of DSSCs.....	27
1.1.2.3	Organic dyes for DSSCs	29
1.1.2.4	Design of metal-free sensitizers.....	31
1.2	Summary and motivation.....	39
1.3	References.....	40
Chapter 2	Synthesis and Characterization of	
	Benzodithieno[3,2-<i>b</i>]thiophenes for Organic Field Effect Transistors	55
2.1	Introduction.....	55
2.2	Synthesis	57
2.3	Results and discussion	59
2.3.1	Thermal properties	59
2.3.2	Linear optical characterization.....	60
2.3.3	Electrochemical characterization.....	60

2.3.4	Device properties for OFETs	63
2.3.5	XRD and AFM characterizations.....	66
2.4	Conclusion	70
2.5	Experimental.....	70
2.5.1	General procedure and requirements	70
2.5.2	Synthetic procedures.....	72
2.6	References.....	86
Chapter 3	Naphthodithiophene-based D-A-D-A-D Type Oligomer for Organic Field Effect Transistors	88
3.1	Introduction.....	88
3.2	Synthesis	90
3.3	Results and discussion	96
3.3.1	Thermal properties	96
3.3.2	Linear optical characterization.....	96
3.3.3	Electrochemical characterization.....	98
3.3.4	Field effect transistor properties	100
3.3.5	XRD and AFM characterization	103

3.4	Conclusion	105
3.5	Experimental	106
3.5.1	General requirements and procedures.....	106
3.5.2	Synthetic procedures.....	108
3.6	References.....	132
Chapter 4	Efficient Naphthodithieno[3,2-<i>b</i>]thiophene-based Photosensitizers for Dye-Sensitized Solar Cells	135
4.1	Introduction.....	135
4.2	Synthesis	137
4.3	Characterization	142
4.3.1	Characterization of photosensitizers	142
4.3.1.1	Thermal stability	142
4.3.1.2	Optical properties.....	143
4.3.1.3	Electrochemical properties	144
4.3.1.4	Electronic structures	146
4.3.2	Cell device fabrication and characterization.....	147
4.3.2.1	Fabrication of DSSCs	147

4.3.2.2	Characterization for DSSCs.....	148
4.4	Conclusions.....	159
4.5	Experimental.....	160
4.5.1	General procedures and requirements.....	160
4.5.2	Synthetic procedures.....	162
4.6	References.....	181
Chapter 5	Synthesis and Characterization of	
	Benzodithienothiophene-based Photosensitizers for DSSC Application	184
5.1	Introduction.....	184
5.2	Synthesis	187
5.3	Results and discussion	192
5.3.1	Thermal properties	192
5.3.2	Linear optical properties	193
5.3.3	Electrochemical properties	195
5.3.4	Computation.....	197
5.3.5	Cell device fabrication and characterization.....	199
5.3.5.1	Fabrication of DSSCs	199

5.3.5.2	Photovoltaic characterization.....	200
5.3.5.3	Charge transfer and recombination.....	202
5.4	Conclusion	205
5.5	Experimental.....	206
5.5.1	General requirements and procedures.....	206
5.5.2	Synthetic procedures.....	207
5.6	References.....	225
Chapter 6	Concluding Remarks	229
Appendix I	¹H NMR Spectra of Selected Novel Synthesized Compounds ...	232
Appendix II	¹³C NMR Spectra of Selected Novel Synthesized Compounds.	243
Appendix III	HR-MS Spectra of Selected Novel Synthesized Compounds..	253
Curriculum Vitae.....		265