

## DOCTORAL THESIS

### Synthesis of carbon-free Bi2223 superconductor of high phase purity

Li, Chaorui

*Date of Award:*  
1998

[Link to publication](#)

#### General rights

Copyright and intellectual property rights for the publications made accessible in HKBU Scholars are retained by the authors and/or other copyright owners. In addition to the restrictions prescribed by the Copyright Ordinance of Hong Kong, all users and readers must also observe the following terms of use:

- Users may download and print one copy of any publication from HKBU Scholars for the purpose of private study or research
- Users cannot further distribute the material or use it for any profit-making activity or commercial gain
- To share publications in HKBU Scholars with others, users are welcome to freely distribute the permanent URL assigned to the publication

# Synthesis of Carbon-Free Bi2223 Superconductor of High Phase Purity

LI Chao Rui

A thesis submitted in partial fulfillment of the requirements  
for the degree of  
Doctor of Philosophy

February 1998

Hong Kong Baptist University

## ABSTRACT

$\text{Bi}_2\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_{10+\delta}$  (Bi2223) is a high- $T_c$  superconducting ceramic and this work is devoted to the synthesis of its high purity phase. In the past decade, although Tl- and Hg-based systems with higher  $T_c$  have been synthesised, their chemical toxicities limit their application potentials, hence Bi2223 remains one of the most promising materials, despite problems with attaining its pure phase, which is due to the uncertainty in its formation mechanism and the effect of residual carbon impurities. In this work, a four-step process has been developed, in which carbon-free intermediate compounds are fabricated by solid-state reaction. A series of thermoanalytical measurements had been performed on a large group of powder samples, with different combinations and proportion of the source chemicals  $\text{Bi}_2\text{O}_3$ ,  $\text{SrCO}_3$ ,  $\text{CaCO}_3$  and  $\text{CuO}$ . Decomposition of Sr carbonate is activated in the mixture with precursor-A  $\text{Bi}_2\text{CuO}_4$  from  $\text{Bi}_2\text{O}_3$  and  $\text{CuO}$ . Two types of  $\text{Bi}_2\text{CuO}_4$ , with similar phase structure, are produced, and their respective effects on  $\text{SrCO}_3$  have been identified. Then precursor-B, containing predominant Bi2201 and minor  $\text{Bi}_2\text{Sr}_2\text{O}_5$ , is formed. Precursor-C, a mixture of  $\text{Ca}_2\text{CuO}_3$  and  $\text{CuO}$ , comes from the chemical reaction between  $\text{CaCO}_3$  and  $\text{CuO}$ . All products and intermediates have successfully been identified with powder XRD.

For the exactly analysis of the kinetics of solid-state reaction, a new method has been developed. Its validity is experimentally confirmed.

Bi(Pb)2223 superconducting materials are synthesised using carbon-free precursors-B and -C as source chemicals. Based on TA and XRD data, an optimum procedure is formulated. In our precursor route,  $\text{Bi}_2\text{Sr}_2\text{O}_5$  plays an important role in progressing toward highly pure Bi2223. The superconductivity and phase purity of processed materials are carried out. Although it is difficult to achieve pure Bi2223 in the nominal composition  $\text{Bi}_{2.0}\text{Sr}_{2.0}\text{Ca}_{2.0}\text{Cu}_{3.0}\text{O}_{10+\delta}$ , kinetics analysis suggests diffusion-controlled growth in  $\text{Bi}_{1.84}\text{Pb}_{0.16}\text{Sr}_{1.84}\text{Ca}_{2.12}\text{Cu}_{3.04}\text{O}_{10+\delta}$  and  $\text{Bi}_{2.0}\text{Sr}_{1.84}\text{Ca}_{2.12}\text{Cu}_{3.04}\text{O}_{10+\delta}$ , which two compositions can be synthesised as carbon-free and phase-pure.

# CONTENTS

DECLARATION	i
ABSTRACT	ii
ACKNOWLEDGMENTS	iii
CONTENTS	iv
LIST OF TABLES	viii
LIST OF FIGURES	ix
<b>Chapter 1 Introduction</b>	<b>1</b>
1.1 Purpose of the Research Project	1
1.2 Brief Historical Perspectives	2
1.2.1 Superconducting Characteristic Properties	2
1.2.1.1 Zero resistance: $\rho = 0$ for $T < T_c$	4
1.2.1.2 Perfect diamagnetism: $B = 0$ inside the superconductor	6
1.2.2 Type-I and Type-II Superconductors	9
1.2.3 Superconducting Materials	14
1.3 Overview on Formation of Bi2223 Phase	17
1.3.1 Growth Conditions	17
1.3.1.1 Starting composition	17
1.3.1.2 Calcination atmosphere	17
1.3.1.3 Calcination temperature	18
1.3.1.4 Calcination time	18
1.3.2 Mechanisms	19
1.3.2.1 Disproportionation	20
1.3.2.2 Diffusion and cation insertion (from liquid)	21
1.3.2.3 Dissolution-precipitation (Peritectic-like reaction)	22
1.3.2.4 Liquid-aided sintering ( $\text{Ca}_2\text{PbO}_4$ -catalyzed reaction mechanism)	24
1.3.2.5 Roles of Pb	25
1.3.3 Kinetics	26
1.3.4 Key Elements	28

<b>Chapter 2 Procedures of Materials Fabrication</b>	<b>32</b>
2.1 Solid-State Reaction	35
2.1.1 Calcination	36
2.1.2 Modification of a Muffle Furnace	38
2.1.3 Sintering	41
2.1.4 Control of Atmosphere	44
2.2 Precursor Routes	46
<b>Chapter 3 Characterisation of Processed Materials</b>	<b>48</b>
3.1 Thermal Analysis	49
3.2 X-ray Diffraction	60
3.2.1 X-ray Diffraction Data Acquisition	63
3.2.2 X-ray Diffraction Data Analysis	63
3.2.3 Kinetic Study Using X-ray Diffraction	68
3.3 Identification of Superconductivity	70
3.3.1 Four-Point Probe Technique	71
3.3.2 Magnetic Susceptibility	72
3.3.3 Cryogenic System	76
3.3.4 Data Acquisition	78
<b>Chapter 4 A New Method for Analysing TA Data from Solid-State Reaction</b>	<b>81</b>
4.1 Introduction	81
4.2 Theory	83
4.3 Applications	87
4.3.1 Strontium Carbonate Data	88
4.3.2 Calcium Carbonate Data	93
4.3.3 Copper Oxide Data	97
4.3.4 Data from ICTAC for Kinetics Analysis Project	100
4.4 Conclusions	104

<b>Chapter 5 Carbon-Free Precursors for Bi(Pb)2223</b>	<b>107</b>
5.1 Introduction	107
5.2 Experimental Details	108
5.3 Results and Discussion	112
5.3.1 Thermal Analysis on Quaternary Mixture	112
5.3.2 Decomposition of CaCO <sub>3</sub> in Powder Mixtures	115
5.3.2.1 CaCO <sub>3</sub> + CuO binary powder mixture	118
5.3.2.2 CaCO <sub>3</sub> + Bi <sub>2</sub> O <sub>3</sub> binary powder mixture	119
5.3.2.3 CaCO <sub>3</sub> + SrCO <sub>3</sub> binary powder mixture	119
5.3.2.4 2CaCO <sub>3</sub> + Bi <sub>2</sub> O <sub>3</sub> + CuO ternary powder mixture	120
5.3.3 Decomposition of SrCO <sub>3</sub> in Powder Mixtures	122
5.3.3.1 SrCO <sub>3</sub> + CuO binary powder mixture	125
5.3.3.2 SrCO <sub>3</sub> + Bi <sub>2</sub> O <sub>3</sub> binary powder mixture	126
5.3.3.3 SrCO <sub>3</sub> + CaCO <sub>3</sub> binary powder mixture	126
5.3.3.4 2SrCO <sub>3</sub> + Bi <sub>2</sub> O <sub>3</sub> + CuO ternary powder mixture	127
5.3.4 Synthesis of Precursor-A Bi <sub>2</sub> CuO <sub>4</sub> and Uncertainty of (Bi, Pb) <sub>2</sub> CuO <sub>4</sub>	129
5.3.4.1 Bi <sub>2</sub> O <sub>3</sub> + CuO binary powder mixture	129
5.3.4.2 Uncertainty of (Bi, Pb) <sub>2</sub> CuO <sub>4</sub>	134
5.3.5 Carbon-Free Precursor-B	137
5.3.5.1 2SrCO <sub>3</sub> + Bi <sub>2</sub> CuO <sub>4</sub> (black) powder mixture	137
5.3.5.2 2SrCO <sub>3</sub> mixed with Bi <sub>2</sub> CuO <sub>4</sub> (gray) or (Bi, Pb) <sub>2</sub> CuO <sub>4</sub>	140
5.3.5.3 SrCO <sub>3</sub> mixed in Bi <sub>2</sub> CuO <sub>4</sub> (black) with various mass ratio	140
5.3.5.4 SrCO <sub>3</sub> mixed with Bi <sub>2</sub> O <sub>3</sub>	143
5.3.6 Carbon-Free Precursor-C	146
 <b>Chapter 6 Synthesis of Bi(Pb)2223 of High Phase Purity</b>	 <b>151</b>
6.1 Introduction	151
6.2 Experimental Procedures	152
6.3 Results and Discussion	154
6.3.1 Synthesis of Bi(Pb)2223 Phase	157

6.3.2 Synthesis of Bi2223 Phase	164
6.3.3 Phase Formation Kinetics	169
<b>Chapter 7 Conclusions</b>	<b>171</b>
<b>References</b>	<b>177</b>
<b>VITAE</b>	<b>183</b>