

## DOCTORAL THESIS

### Superlens design and fabrication

Li, Guixin

*Date of Award:*  
2009

[Link to publication](#)

#### General rights

Copyright and intellectual property rights for the publications made accessible in HKBU Scholars are retained by the authors and/or other copyright owners. In addition to the restrictions prescribed by the Copyright Ordinance of Hong Kong, all users and readers must also observe the following terms of use:

- Users may download and print one copy of any publication from HKBU Scholars for the purpose of private study or research
- Users cannot further distribute the material or use it for any profit-making activity or commercial gain
- To share publications in HKBU Scholars with others, users are welcome to freely distribute the permanent URL assigned to the publication

# **Superlens Design and Fabrication**

**LI Guixin**

A thesis submitted in partial fulfillment of the requirements  
for the degree of  
Doctor of Philosophy

**Principle Supervisor: Prof. CHEAH Kok Wai**

Hong Kong Baptist University

September 2009

# Abstract

Superlens has been scientists' interests in recent years. It is known for overcoming the optical diffraction limit by collecting propagating and evanescent waves through negative index materials. Under quasi-static limit, a slab of material with negative permittivity will act as superlens. On the basis of this principle, the superlens based on silver/dielectric multilayer was studied from theoretical and experimental perspectives in this work.

In the theoretical work, the anisotropic superlens with hyperbolic dispersion relation and the resonant cavity superlens were studied. The hyperbolic dispersion means that there is no cutoff value for high spatial components, a slab lens made of such kind of medium could convert evanescent waves into propagating ones through the surface coupling modes and thus has a super or even perfect resolution. One application is the near-field superlens consisting of complementary meta-materials, in which the diffraction effects in first slab are compensated in the second slab which has a complementary anisotropic permittivity. By tuning the effective permittivity in the complementary meta-materials, a near field superlens with tunable working wavelength and working distance could be realized. The second application is the far-field superlens (FSL) with coupled Fabry-Perot cavities, in which the image sub-diffraction objects can be transferred to the outer surface of FSL and resolved by the optical microscope. Meanwhile, high transmittance and good image fidelity in this far field superlens could be realized.

The resonant superlens proposed by J. Li et al. [100] was investigated and compared with the single silver layer superlens and the silver/dielectric multilayer superlens from an experimental point of view. In the experimental work, these near-field superlens devices were fabricated, the transmission and near-field imaging property of them were physically characterized.

Firstly, the angle resolved transmission experiment (ART) was used to measure the transmission properties of propagating waves in the three kinds of superlens devices,

the results show that resonant superlens with Fabry-Perot cavity has an omni-directional transmission property and high transmission efficiency for the p-polarized light. In comparison, the single silver layer superlens and the multilayer superlens have low transmission efficiency at the working wavelength. All experimental results agree well with simulation results.

The second experimental step is near field-imaging process. Commercial photolithographic technique was utilized to demonstrate the resonant superlens property. The superlens mask with various resolutions was fabricated by focused ion beam, and the superlens devices with optimized surface were fabricated on the superlens mask through the thin film deposition method. The sub-wavelength imaging resolution was realized in the resonant superlens, the single silver layer superlens and the multilayer superlens, of which the resonant superlens has higher imaging contrast and higher image fidelity. These results also agree well with theoretical predictions.

# Table of Contents

Declaration.....	i
Abstract.....	ii
Acknowledgements.....	iv
Table of Contents.....	vi
List of Figures.....	ix
List of Tables.....	xviii
Chapter 1 Introduction.....	1
1.1 Negative Refraction in Metamaterials.....	2
1.2 Near Field Superlens.....	9
1.2.1 Theory of Near Field Superlens.....	10
1.2.2 The Quasi-static Limit and Superlens.....	12
1.2.3 Superlens with Metal-Dielectric Multilayer Medium.....	14
1.2.4 Experimental Realization of Superlens.....	15
1.3 Far Field Superlens.....	16
1.3.1 Far Field Superlens in Anisotropic Meta-materials.....	17
1.3.2 Far Field Superlens Based on Silver Superlens.....	21
1.3.3 Far Field Optical Microscopy through other Strategies.....	21
1.4 Negative Refraction in Photonic and Acoustic Crystals.....	23
1.4.1 Negative Refraction in Photonic Crystal.....	23
1.4.2 Negative Refraction in Acoustic Crystal.....	24
1.5 Our Work in Superlens.....	26
Chapter 2 Superlens in Anisotropic Metamaterials.....	27
2.1 Complementary Anisotropic Superlens.....	27
2.1.1 Introduction.....	27
2.1.2 Anisotropic Superlens.....	28
2.1.3 Results and Discussions.....	32
2.1.4 Summary.....	33
2.2 Half-Cylindrical Far Field Superlens with Coupled Fabry-Perot Cavities.....	35
2.2.1 Introduction.....	35
2.2.2 Theory of Far Field Superlens.....	36

2.2.3 Results and Discussions .....	38
2.2.4 Summary .....	41
2.3 Transfer Matrix Method .....	42
2.3.1 Theory of Transfer Matrix Method .....	42
2.3.2 Transfer Matrix Method for Evanescent Waves.....	45
2.4 Finite Element Method .....	48
2.4.1 Model Setup .....	48
2.4.2 Boundary Conditions .....	49
2.4.3 Sub-Domain Setting.....	49
2.4.4 Computing and Post-Processing .....	50
2.5 Summary .....	51
Chapter 3 Theoretical Simulation of Resonant Superlens .....	52
3.1 Introduction.....	52
3.2 Superlens Devices .....	53
3.2.1 Ag/SiO <sub>2</sub> /Ag Resonant F-P cavity .....	53
3.2.2 Transmission in Resonant Superlens .....	58
3.2.3 Transmission in Single Ag Layer.....	60
3.2.4 Transmission in Ag/SiO <sub>2</sub> Multilayer Superlens .....	61
3.2.5 PMMA Device .....	62
3.3 Evanescent waves in the Superlens Devices.....	63
3.4 Imaging Simulation.....	66
3.5 Summary .....	71
Chapter 4 Experiment .....	72
4.1 Mask Fabrication .....	72
4.1.1 Electron-Beam Lithography Method .....	73
4.1.2 The Nano-Imprint Lithography Method .....	73
4.1.3 Focused Ion Beam Method .....	74
4.2 Thin Film Evaporation .....	78
4.2.1 Thermal Evaporation.....	78
4.2.2 E-Beam Evaporation.....	79
4.2.3 Radio Frequency (RF) Magnetron Sputtering .....	80
4.3 Surface Planarization .....	81
4.4 Photolithography .....	84
4.4.1 Sample Cleaning .....	84

4.4.2 Photoresist Application .....	84
4.4.3 Mask Aligner and Exposure.....	85
4.4.4 Pattern Development.....	87
4.5 Physical Characterization.....	88
4.5.1 Optical Inspection Microscope .....	88
4.5.2 Atomic Force Microscope.....	88
4.6 Angle Resolved Transmission.....	90
4.7 Summary .....	92
Chapter 5 Results and Discussions .....	93
5.1 Angle Resolved Transmission (ATR).....	93
5.1.1 Transmission in Resonant Superlens .....	94
5.1.2 Transmission in Single Ag Layer Superlens .....	96
5.1.3 Transmission in Ag/SiO <sub>2</sub> Multilayer Superlens .....	98
5.2 Atomic Force Microscope Results .....	102
5.2.1 Resonant Cavity Experiment .....	103
5.2.2 Single Ag Layer Superlens.....	110
5.2.3 Ag/SiO <sub>2</sub> Multilayer Superlens.....	116
5.2.4 Control Experiment.....	122
5.3 Summary .....	128
Chapter 6 Conclusions .....	129
References.....	132
Publications and Conference Presentations .....	137
Curriculum Vitae.....	138